



# LATEX-ITE ACRYLIC RESURFACER

## PRODUCT SPECIFICATIONS

### Description and Usage

*Latex-ite* Acrylic Resurfacer is a heavy-bodied acrylic emulsion for use on open graded or pitted asphalt or concrete surfaces. It is installed prior to the application of the *Latex-ite* Acrylic Color System. Application of the *Latex-ite* Acrylic Resurfacer provides an economical means for filling voids and pits in new and previously coated asphalt and concrete surfaces. *Latex-ite* Acrylic Resurfacer may also be used to level birdbaths or minor depressions prior to coating.

### Mix Design

Mix thoroughly to insure uniform consistency.

	<u>Patching</u>	<u>Coating</u>
<i>Latex-ite</i> Acrylic Resurfacer	5 gals.	55 gals.
Portland 1A Cement	1/2-1 gal.	-0-
Potable Water	0-1 gal.	24-30 gals.
60 mesh, clean, dry, Silica Sand	50-100 lbs.	-0-
80-100 mesh, clean, dry, Silica Sand	-0-	300-500 lbs.

### Application

Refer to the Court Surface Guideline for surface preparation procedures. Application requires the use of a 24" to 48" long, flexible, 50 to 70 durometer, rubber squeegees of good quality and in good condition.

### Coverage

.04 to .08 gallon per square yard. Coverage rate will vary depending upon surface porosity.

### Drying Time

30 to 90 minutes in optimum conditions. Humidity, surface temperature, and ambient temperature will affect drying process.

### Limitations and Precautions

*Latex-ite* Acrylic Resurfacer should not be applied when the ambient temperature is below 50° F or when surface temperature is above 140° F. Do not apply when rain is imminent. Do not store in direct sunlight. Keep from freezing.