



LATEX-ITE ACRYLIC CRACK AND LEVELING COMPOUND

PRODUCT SPECIFICATIONS

Description and Usage

An acrylic emulsion mixed at the jobsite to repair cracks or "birdbaths". A three component system, *Latex-ite* Acrylic Crack and Leveling Compound is used to fill and level both surface and structural cracks, as well as "birdbaths". Prior to the application of the *Latex-ite* Acrylic Color System, thoroughly clean all cracks and apply the *Latex-ite* Acrylic Crack and Leveling Compound. When used for "birdbath" patching, thoroughly clean the area to be levelled.

Application

Apply directly into clean, dry cracks with a steel hand trowel.

For leveling "birdbaths" use a rubber faced squeegee or straightedge.

NOTE: Allow 24 hours curing time before applying additional coatings.

Mix Design

Latex-ite Acrylic Crack and Leveling Compound.....1 Gallon
80 - 100 mesh, clean dry Silica Sand2 Gallons
Portland 1A Cement1/4 gallon

Blend the silica sand with the cement in a clean mortar mixer or by use of a hand drill. Add *Latex-ite* Acrylic Crack and Leveling Compound while mixing. Mix until there is uniform consistency. If the mix appears too dry, add additional *Latex-ite* Acrylic Crack and Leveling Compound until a creamy consistency is obtained. Upon completion of mixing apply to cracks or low areas immediately.

Never Add Water

Clean equipment and tools immediately after completion.

Coverage

CRACK: One (1) gallon of mixed emulsion. Approximately 8 - 10 linear feet of crack measuring 1/4" wide by 3/4" to 1" deep.

PATCH: Quantities will vary with size and depth of "birdbath".

Drying Time

Mixed material dries rapidly. Actual drying time will vary according to width and depth of crack or patch. Humidity, surface temperature, and ambient temperature will affect drying process.

Limitations and Precautions

Latex-ite Acrylic Crack and Leveling Compound should not be applied when the ambient temperature is below 50° F or when surface temperature is above 140° F. Do not store in direct sunlight. Keep from freezing. Do not apply when rain is imminent.

(OVER)



131 Willow St. Cheshire, CT 06410

203.272.3221

Toll Free 888.711.7483

Fax 203.271.3396